

Pakull

Compressable slabs. CE marked. Packed in transparent PE-foil.



Usage

Heat insulation in roofs, where the insulation will not be subjected to pressure or loads. Has good sound insulation properties. Should not be used where temperature is above 100 °C.

Technical information

							
Nominal	Compressive Strength	Thickness Tolerances	Temp. Tolerances	Thermal Conductivity	Reaction to Fire	Short Term Water Absorption	CE - Marked
kg/m ³	kPa	Class	°C	W / mK	Euroclass	kg/m ²	Standard
30	NPD	T2	100	0,037	F	≤1	
	IST EN 826	IST EN 823		IST EN 12939	IST EN 13501-1	IST EN 1609/12087	EN13162

NPD - No Performance Determined

Size, Packing Specification and Thermal Resistance

Size			Pack		Pallet			Thermal Resistance
THICKNESS	WIDTH	LENGTH	SLABS	M ²	PACK	M ²	M ³	M ² K / W
180	560	1200	4	2,69	24	64,51	6,86	4,85
200	560	1200	4	2,69	24	64,51	6,84	5,40
220	560	1200	4	2,69	24	64,51	6,82	5,90

Other sizes can be produced and packed

Quality Control

The production at Sauðárkrókur follows a documented quality system verified according to ISO 9001 and environmental system according to ISO 14001.