



OSB 3 ECOBOARD

The universal OSB panel

DESCRIPTION

OSB 3 ECOBOARD is a high-performance wood-based panel which complies with EN 300/EN 13986. It is available in multiple formats with a tongue and groove profile on all 4 sides or with butt edges, with a Contiface surface (treated, not sanded) or in a sanded surface version. OSB 3 offers excellent results in the construction sector and can be used as a multipurpose panel for structural purposes and for load-bearing and in roof, wall and floor areas. It can be used as an airtight layer or vapour barrier in a vapour permeable construction, so that the use of additional veneer is unnecessary.

- OSB panel for load-bearing purposes in humid conditions (service class 1 + 2)
- High strength and stability
- Suitable as an airtight layer or vapour barrier
- Non-detrimental to health - independent confirmation that it is safe to use with foodstuffs
- Abrasion-resistant, dirt and water-repellent Contiface surface
- Formaldehyde-free and moisture-proof gluing
- High quality confirmed by regular, external inspections
- Raw material exclusively from responsible forest and timber industry

PROPERTIES



DURABILITY



VERSATILITY



VERY LOW
EMISSIONS



MOISTURE
RESISTANT



LOAD-BEARING

APPLICATIONS

- Floor construction
- Wall cladding
- Structural wall elements and roof panelling
- Housing, industrial and formwork construction
- Transport packaging



FLOORING



FOR PANELING



FOR
CONSTRUCTION

OSB 3 ECOBOARD

The universal OSB panel

TECHNICAL DATA

PROPERTIES	UNIT	THICKNESS RANGE (mm)			
		6 - 10	> 10 - < 18	18 - 25	> 25 - 32
Bulk density	Kg/m ³	≥ 600			
Rated thermal conductivity λ _R	W/(m*K)	0.13			
Formaldehyde emission	Class	E1 - formaldehyde-free glued (<0.03 ppm)			
Fire reaction	Class	D-s2, d0 * ¹			
Thickness swelling (24 hours)	%	15			
Change in length per 1% change in moisture content	%	0.03			
Bending strength - major axis	N/mm ²	22	20	18	16
Bending strength - minor axis	N/mm ²	11	10	9	8
Modulus of elasticity (MOE) - major axis	N/mm ²	3500	3500	3500	3500
Modulus of elasticity (MOE) - minor axis	N/mm ²	1400	1400	1400	1400
Internal bond	N/mm ²	0.34	0.32	0.30	0.29
Internal bond after boil test	N/mm ²	0.15	0.13	0.12	0.06

CHARACTERISTIC VALUES*²

PROPERTY	UNIT	THICKNESS (mm)	BENDING f _m		TENSION f _t		COMPRESSION f _c		PANEL SHEAR f _v	PANEL SHEAR f _v
			or 0	⊥ or 90	or 0	⊥ or 90	or 0	⊥ or 90		
STRENGTH	N/mm ²	6 - 10	18.0	9.0	9.9	7.2	15.9	12.9	6.8	1.0
		> 10 - 18	16.4	8.2	9.4	7.0	15.4	12.7		
		> 18 - 25	14.8	7.4	9.0	6.8	14.8	12.4		
PROPERTY	UNIT	THICKNESS (mm)	BENDING f _m		TENSION f _t		COMPRESSION f _c		PANEL SHEAR G _v	PANEL SHEAR G _v
			or 0	⊥ or 90	or 0	⊥ or 90	or 0	⊥ or 90		
STIFFNESS	N/mm ²	6 - 25	4930	1980	3800	3000	3800	3000	1080	50

*¹ for thicknesses of 9 mm or more; for thicknesses of 6 to 9 mm: fire reaction Class E; *² acc. to EN 12369-1.

ALSO AVAILABLE IN:



Promoting
Sustainable Forest
Management
www.pefc.org

CERTIFICATIONS:



All the product names and company names used in this data sheet are trade names and / or registered trademarks belonging to the respective proprietors. Any reproduction requires the express authorisation of Sonae Arauco and / or the respective trademark proprietor. Sonae Arauco assumes no liability for any possible errors in this prospectus. This technical data sheet reflects the current technical specifications at the time of print and will be superseded by any new edition. Our detailed instructions for use must be observed. The respective building regulations must be complied with. It is important to check the material's suitability for the intended purpose. Version: August 2017