

LION HD PANEL BOARD™

Introduction

LION HD Panel Board™ is oil tempered hardboard with smooth face and edges painted. Mesh pattern reverse side. Lion HD Panel Board™ is suitable for the internal lining of agricultural buildings, hoardings, shopfitting, site protection and general building work.

Standard colour of the paint is white, but other colours are also available, subject to quantity.

Specification

Product identification code	OTSW*
Thickness [mm]	6
Standard sizes [mm]	1200 x 2745
Standard pallet sizes	6,0 mm 50 sheets
Packing	Disposable wooden pallet bottom Plastic bands
Paint	Water based acrylate paint in smooth side and edges

Technical properties and performance

Property	Unit	Thickness		
		≤ 3,0 to 3,5 mm	> 3,5 to 5,5 mm	> 5,5 mm
Density	kg/m ³	≥ 900		
Dimensional tolerances				
<i>Thickness</i>	mm	± 0,3 mm	± 0,5 mm	± 0,7 mm
<i>Width / length</i>	mm	± 2,0 mm/m, max ± 5 mm		
<i>Squareness</i>	mm/m	2,0 mm/m		
<i>Edge straightness</i>	mm/m	1,5 mm/m		
Bending strength	N/mm ²	35	32	30
Internal bond	N/mm ²	0,60	0,60	0,30
Swelling in thickness (24h)	%	25	20	20
Release of Formaldehyde	Class	E1		
Moisture content	%	4-9 %		

Product standards

EN 622-1 Fibreboards. Specifications. Part 1: General Requirements.

EN 622-2 Fibreboards. Specifications. Part 2: Requirements for hardboards.

EN 13986:2004+A1:2015 Wood based panels for construction. Characteristics, evaluation of conformity and marking

Type HB.H. General purpose board for use in humid conditions

Certificates



CE marked in accordance with requirements of EN 13986:2004+A1:2015 standard



The classification presents emission requirements for the building materials, fixture and furniture without padding or textile coverings used in ordinary work spaces and residences with respect to good indoor air quality. M1 stands for low emissions. m1.rts.fi/en




PEFC certificate: Promoting sustainable forest management

Handling and Storage

Panels should preferably be stored in an enclosed dry building. Where temporary storage outside cannot be avoided, then stacks should be covered with waterproof but vapour permeable sheeting, keeping all panels on raised bearers to prevent contact with the ground, water or vegetation. Any protective wrapping should be kept in place as long as possible prior to conditioning for use.

Panels should be stacked flat on a level surface with all four edges flush. The ideal base is a close boarded or slatted pallet. If this is not possible the panels should be carefully stacked on battens of equal thickness at centres not exceeding 600 mm.



Stacking on edge should be avoided whenever possible. Where space will only permit edge stacking then the edges should not be permitted to come into direct contact with the floor to avoid possible moisture pick-up or damage to the edges.

Panels should not be leant against walls but supported by a braced, purpose made rack using thick (>18 mm) base and back panels.

ATTACHMENTS

Declaration of Performance No. FF2CPRHB.H

Suomen Kuitulevy Oy
Finnish Fibreboard Ltd
PL 4, FI-18101 Heinola, Finland
Tel. +358(0) 20 110 3300
Fax +358(0) 20 110 3307

Y-tunnus/Business ID
1503858-9

etunimi.sukunimi@finfib.fi
firstname.surname@finfib.fi

VAT No.
FI 15038589

www.suomenkuitulevy.fi
www.finnishbreboard.com

Kotipaikka / Domicile:
Heinola