

157502AN - Diffusionsöppen Skarvtejp

Description	Denna enkelhäftande tejp består av en flerlayers PP-nonwovensväv belagd på en sida med ett dispersionsbaserat modifierad akrylhäftämne. Tejpen ligger på en vit papperslinier.
Product properties	Tejpen har mycket god resistens mot UV-ljus, fukt, vatten, åldring och temperatur. Den har mycket god vidhäftning mot de flesta material, också ojämna och strukturerade ytor. Den är UV-resistent i upp till 3 månader.
Applications	Tejpen är avsedd för försegling av diverse skarvar eller anslutningar utomhus, exempelvis runt dörrar, fönster eller andra håltagningar på husstommens / fasadens utsida, där man med hjälp av tejpen kan täta och uppnå ett gott väderskydd (regn- och vindtäthet). Applicerad / monterad kan den muras, putsas eller målas över med en dispersionsfärg.
Storage and ageing	1 års lagringstid om produkten förvaras i originalemballage och i normal rumstemperatur, skyddad mot solljus.
Applying tips	Ytan ska vara ren och torr och fri från fett, damm och smuts. Tejpen ska appliceras med erforderligt tryck.
Additional technical properties	Vattentäthet: W1 i enlighet med EN 1928. SD-värde: 1.03 m. Luftgenomsläpplighet: < 0.01 m ³ / (h x m ²)

TECHNICAL DATA

Weather resistant	Yes	
UV resistant	Yes	
Aging resistant	Yes	
Color	Anthracite	
Thickness total	0.5 mm	19.685 Mils
Adhesion on SS	35 N/25mm	7.99 Lbs/inch
Tensile strength length	75 N/25mm	17.13 Lbs/inch
Tensile strength width	55 N/25mm	12.56 Lbs/inch
Elongation length	80 %	
Elongation width	80 %	
Service temperature	Between -40 and 80 °C	Between -40 and 176 °F
Application temperature	Between -5 and 35 °C	Between 23 and 95 °F

Disclaimer: Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available "as is" and that Stokvis Tapes, an ITW company, gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information. See our applicable delivery conditions. Each user should conduct his own tests to determine the suitability of the product for his intended use and shall assume all risks and liability in connection therewith. Stokvis Tapes cannot be held liable for any damages resulting from the unsuitability of the product. Many factors beyond the control of Stokvis Tapes may affect the use and performance of the product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the Stokvis Tapes product to determine whether it is fit for a particular purpose and suitable for the user's method of application. The information is available to the user for viewing, copying and distributing, provided that Stokvis Tapes, an ITW company, is always quoted as the source. The information is intended solely for informational and non-commercial use. Intellectual property: Stokvis Tapes, an ITW company, reserves all rights regarding this document and the information contained herein. Reproduction, use or disclosure to third parties without express permission is strictly forbidden.

Stokvis Tapes Sverige AB
Zinkgatan 6
Box 769
601 17 Norrköping

+46 - (0)11 280400
www.stokvistapes.se
info@stokvistapes.se
An Illinois Tool Works Company