



## Report of Salt Spray Chamber test

Product	ADBS Hex washer head $\phi$ 7.5x100 ruspert coating (SSW)		
Test Date	2019.03.18		
Test time	From am:10:00 Mar.18~ am:10:00 Apr.28 ; Total:1008 hours		
Quality of Sodium Chloride	reagent first grade		
Quality of distilled water	Aqua pura		
Spraying Apparatus	Fallout	1.0 mL/80cm <sup>2</sup> /h	
	Salt Concentrate	5.0	%
	PH Value	6.5~7.2	
Pressure of compressed air	1.0	Kgf/cm	
Compared Humidity in the test room	96	%	
Temperature Of saturated bucket	35.0	°C	
Temperature of Pressure bucket	47.0	°C	
Temperature of saltwater bucket	35.0	°C	
Extra Comment			
Samples specification	ADBS Hex washer head $\phi$ 7.5x100 ruspert coating		
Test result	No red rust be found on the head part after 1000 hours of salt spray test.		
Q.C. Dept.:	Recorder : Water Ke		
Remark: Test status is enclosed herewith			

0h



24h



699h



1008h

