

Ytelseserklæring	
Referanse: Isola Sveiseoverlag	
Dato: 2015 03 26 Versjon: 2	
Identifisering av produkt: Isola Sveiseoverlag, se produktets emballasje.	
Fabrikkproduksjonskontroll utført av Sintef nr. 1071-CPD-1100	
AVCP 2+	
NS-EN 13707: 2013	Isola as N-3945 Porsgrunn, Norway
Vesentlige egenskaper	Ytelse
Sikkerhet mot brann	Froof *
Egenskaper ved brannpåvirkning	Klasse F
Vanntetthet	W1
Strekkestyrke	
Maksimal strekkstyrke, langs (N/50 mm)	840 ± 150
Maksimal strekkstyrke, tvers (N/50 mm)	650 ± 30
Forlengelse ved maksimal strekkstyrke, langs (%)	45 ± 10
Forlengelse ved maksimal strekkstyrke, tvers (%)	55 ± 10
Punktering, Statisk last, metode A (kg)	20
Punktering, Slag, metode A (mm)	1250 ≥ 800
Rivstyrke	
Langs (N)	300 ± 30
Tvers (N)	330 ± 30
Styrke i sveis:	
Splatestyrke i skjøt (N/50 mm)	NPD**
Skjærestyrke i skjøt (N/50 mm)	NPD**
Kuldemykhet (°C)	-20
Bestandighet	
Sig etter aldring (°C)	NPD**
Kuldemykhet etter Aldring (°C)	NPD**
Helse- og miljøskadelige kjemikaler (Notat 1 og 2)	Ingen


*EN13501-5

**NPD - Ikke deklart

Notat 1: CPR REACH art. 25. Notat 2: Produktet inneholder ikke asbest eller komponenter av tjære

Produktet er i henhold til krav til ytelse og ovenfor deklarasjon. Ytelseserklæringen er utstedt av produsent under et selvstendig ansvar.

Undertegnet av produsenten Isola as

Navn og tittel	Sted og dato for utstedelse	Signatur
Jørgen Young R&D Manager / Leader FoU	Porsgrunn 2015-03-26	



Declaration of preformance		
Reference: Isola Sveiseoverlag		
Dato: 2015 03 26 Version: 2		
Identification of product: Isola Sveiseoverlag see product packaging		
Flexible reinforced bitumen sheet for roof waterproofing		
Certification of conformity of the factory production control by notified body SINTEF No. 1071-CPD-1100		
AVCP 2+		
NS-EN 13707: 2013		Isola as N-3945 Porsgrunn, Norway
Essential characteristics		Performance
External Fire Performance		Froof *
Reaction To Fire		Class F
Water tightness		W1
Tensile Strength		
Maximum Tensile Force MD**	(N/50 mm)	840 ± 150
Maximum Tensile Force CMD**	(N/50 mm)	650 ± 30
Elongation At Maximum Tensile Force MD**	(%)	45 ± 10
Elongation At Maximum Tensile Force CMD**	(%)	55 ± 10
Resistance To Static Loading Method A	(kg)	20
Resistance To Impact Method A	(mm)	1250 ≥ 800
Resistance To Tearing		
MD**	(N)	300 ± 30
CMD**	(N)	330 ± 30
Joint Strength		
Peel Resistance Of Joints	(N/50 mm)	NPD**
Shear Resistance Of Joints	(N/50 mm)	NPD**
Pliability	(°C)	-20
Durability UV Heat And Water		
Heat Flow After Heat Oven Exposure	(°C)	NPD**
Pliability After Heat Oven Exposure	(°C)	NPD**
Dangerous Substances (Notes 1 & 2)		None

*EN13501-5

** MD - Machine Direction, CMD - Cross Machine Direction

*** NPD - No Performance Determined

Note 1: CPR REACH art.25

Note 2: This product does not contain asbestos or tar constituents

The performance of the product identified is in conformity with the declared performance above. This declaration of performance is issued under the sole responsibility of the manufacturer. Signed for and on behalf of the manufacturer by:

Name and Function	Place and date of issue Signature	Signature
Jørgen Young R&D Manager / Leader FoU	Porsgrunn 2015-01-26	